

Issue Date: 06-09-2015
Revision Date 12-04-2018
Renewal Due: 01-01-2020

DIVISION: 07 00 00 – THERMAL AND MOISTURE PROTECTION
Section: 07 30 05 – Roofing Felt and Underlayment

REPORT HOLDER:

GT Industrial Products Company
600 N 85th Street, Suite C-101
Seattle, WA 98103
(206) 471-0640
www.gti-products.com

REPORT SUBJECT:

GUARDMAX GMX-145 Roofing Underlayment

1.0 SCOPE OF EVALUATION

This Research Report addresses compliance with the following Codes:

- 2018, 2015, and 2012 *International Building Code*® (IBC)
- 2018, 2015, and 2012 *International Residential Code*® (IRC)

2.0 USES

The GUARDMAX GMX-145 roofing underlayment is used in the field of the roof as an alternative to ASTM D226, Type I and Type II roof underlayments specified in Chapter 15 of the IBC and Chapter 9 of the IRC. The underlayment may be used as a component of a classified assembly when installed as described in this report.

The underlayment has been evaluated for the following properties:

PROPERTY	IBC SECTION ¹	IRC SECTION ¹
Physical Properties	104.11, 1506, and 1507	R104.11, R904, and R905
Fire Classification	1505	R902.1

¹ Referenced sections apply to 2018 IBC and IRC

3.0 DESCRIPTION

GUARDMAX GMX-145 is a 4-layer synthetic roofing underlayment, consisting of cross-woven polypropylene base scrim coated both sides, and laminated with non-woven fabric on the top side. Total weight of GMX-145 is 2.97 pounds per 100 square feet. GUARDMAX GMX-145 roofing underlayment

is blue in color on both sides. Standard roll size is 4 feet wide by 250 feet long but is available in custom sizes.

4.0 INSTALLATION

4.1 General:

Installation of the underlayment must comply with the applicable Code, this report, and the report holder’s published installation instructions.

The roofing underlayment must be installed in accordance with the subsections of IBC Section 1507 and IRC Section R905 applicable to the roof covering being installed. The roofing underlayment must be laid with the print side up, with laps as required by the applicable Code, evaluation report, or manufacturer’s instructions, whichever is more restrictive.

The roof covering may be installed immediately following the underlayment application and the underlayment must be covered within the time designated in the report holder’s published installation instructions.

4.2 Ice Barrier:

The GUARDMAX GMX-145 roofing underlayment has not been evaluated for use as an ice barrier. In areas of the roof required by IBC Section 1507 or IRC Section R905 to have an ice barrier, a self-adhering polymer modified bitumen sheet complying with ASTM D1970, or two layers of Code-complying underlayment solidly cemented together must be used such that the ice barrier extends up the roof a minimum distance of 24 inches inside the interior wall line of the building. The roofing underlayment installed in the field of the roof must overlap the ice barrier.

4.3 Fire Classification:

The roofing underlayment may be used as a component of a classified roof assembly when specifically recognized as such in a Listing approved by the Code official. The underlayment may also be used as an alternative to the underlayment specified in the Code for roof coverings permitted under the Exceptions to IBC Section 1505.2 and IRC 902.1, and may be used where non-classified roofing is permitted in IBC Section 1505.5.



5.0 CONDITIONS OF USE

The GUARDMAX GMX-145 roofing underlayment described in this Research Report complies with, or is a suitable alternative to, what is specified in those Codes listed in Sections 1.0 and 2.0 of this report, subject to the following conditions:

5.1 Installation must comply with this Research Report, the manufacturer's published installation instructions, and the applicable Code. In the event of a conflict between the manufacturer's instructions and this report, this report governs.

5.2 Installation is limited to use with approved mechanically attached roof covering systems.

5.3 Installation is limited to roof systems that do not involve hot asphalt or coal-tar pitch.

5.4 Installation is limited to roofs with slope of 2:12 (17%) or greater.

5.5 Attic ventilation must be provided in accordance with the applicable Code since there are no requirements to evaluate vapor permeability of the underlayment.

5.6 In areas of the roof required by IBC Section 1507 or IRC Section R905 to have an ice barrier, an ice barrier must be provided as described in Section 4.2.

5.7 The underlayment is manufactured under a quality control program with inspections by Intertek Testing Services NA Inc. (AA-647).

6.0 SUPPORTING EVIDENCE

6.1 Reports of tests in accordance with ASTM E108.

6.2 Data in accordance with ICC-ES Acceptance Criteria for Roof Underlayments (AC188), dated February 2012 (editorially revised December 2015).

6.3 Intertek Listing Report titled [GT Industry Products Company-GUARDMAX GMX-145 roofing underlayment](#).

7.0 IDENTIFICATION

The GUARDMAX GMX-145 roofing underlayment is imprinted with the product name, the company name (GT Industrial Products Company), the Intertek Mark, and the Code Compliance Research Report number (CCRR-1041). Each roll of the product is also labeled with installation instructions, roll dimensions, and weight.

8.0 OTHER CODES

This section is not applicable.

9.0 CODE COMPLIANCE RESEARCH REPORT USE

9.1 Approval of building products and/or materials can only be granted by a building official having legal authority in the specific jurisdiction where approval is sought.

9.2 Code Compliance Research Reports shall not be used in any manner that implies an endorsement of the product by Intertek.

9.3 Reference to the <https://bpdirectory.intertek.com> is recommended to ascertain the current version and status of this report.

This Code Compliance Research Report ("Report") is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this Report. Only the Client is authorized to permit copying or distribution of this Report and then only in its entirety, and the Client shall not use the Report in a misleading manner. Client further agrees and understands that reliance upon the Report is limited to the representations made therein. The Report is not an endorsement or recommendation for use of the subject and/or product described herein. This Report is not the Intertek Listing Report covering the subject product and utilized for Intertek Certification and this Report does not represent authorization for the use of any Intertek certification marks. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek.

