

Issue Date: 03-02-2018
Revision Date: 12-06-2018
Renewal Date: 03-02-2020

DIVISION: 07 00 00 – THERMAL AND MOISTURE PROTECTION

Section: 07 21 00 – Thermal Insulation

Section: 07 21 19 – Foamed-In-Place Insulation

REPORT HOLDER:

Gaco Western, LLC
1245 Chapman Drive
PO Box 646
Waukesha, WI 53186
262-542-8072
www.gacowallfoam.com

REPORT SUBJECT:

GacoOnePass Low GWP F1880 Spray-applied Polyurethane Insulation

1.0 SCOPE OF EVALUATION

1.1 This Research Report addresses compliance with the following Codes:

- 2018, 2015, 2012, and 2009 *International Building Code*® (IBC)
- 2018, 2015, 2012, and 2009 *International Residential Code*® (IRC)
- 2018, 2015, 2012, and 2009 *International Energy Conservation Code*® (IECC)

NOTE: This report references 2018 Code sections. Earlier versions of the codes may have different section numbers.

1.2 GacoOnePass Low GWP F1880 has been evaluated for the following properties (see Table 1):

- Physical properties
- Surface-burning characteristics
- Thermal resistance
- Air permeability
- Air Barrier
- Moisture Vapor permeance

1.3 The insulation has been evaluated for the following uses (see Table 1):

- Nonstructural thermal insulating material on or in interior and exterior walls, underside of floors, ceilings, and underside of roof decks
- Alternative to Thermal and Ignition Barriers
- Use as air-impermeable insulation
- Use as an air barrier
- Use as a moisture vapor retarder
- Use in Types I, II, III, IV, and V construction under the IBC and construction under the IRC
- Use as exterior duct insulation

2.0 STATEMENT OF COMPLIANCE

GacoOnePass Low GWP F1880 complies with the Codes listed in Section 1.1, for the properties stated in Section 1.2 and uses stated in Section 1.3, when installed as described in this report, including the Conditions of Use stated in Section 6.

3.0 DESCRIPTION

3.1 GacoOnePass Low GWP F1880: GacoOnePass Low GWP F1880 insulation is a closed cell, medium-density, polyurethane foam plastic. The insulation is a two-component, spray-applied foam plastic with a nominal in-place density of 2.2 pcf. The insulation is produced in the field by combining a polymeric isocyanate (A component) with a resin (B component). The insulation liquid components are supplied in 55-gallon drums and 250-gallon totes, and must be stored at temperatures between 40°F and 80°F. The resin (B component) must be protected from freezing temperatures. The insulation has a shelf life of 6 months on the polymeric isocyanate (A component) and 5 months on the resin (B component) when stored in factory-sealed containers at these temperatures.



3.2 DC 315 Intumescent Coating: DC 315 intumescent coating, manufactured by International Fireproof Technology Inc. (IFTI), is a water-based coating supplied in 5-gallon pails and 55-gallon drums. The coating material has a shelf life of 24 months when stored in factory-sealed containers at a temperature between 41°F to 95°F. DC315 complies with ICC-ES AC456 as recognized in Intertek CCRR-1076.

3.3 TPR² Fireshell Coating: TPR² Fireshell F10E coating, manufactured by TPR² Corporation, is a water-based coating supplied in 5-gallon pails and 55-gallon drums. The coating has a shelf life of 1 year when stored unopened at temperatures between 45°F and 95°F. Fireshell F10E complies with ICC-ES AC456 as recognized in ICC-ES ESR-3997.

4.0 PERFORMANCE CHARACTERISTICS

4.1 Surface Burning Characteristics: The insulation, at a maximum thickness of 4 inches and a nominal density of 2.2 pcf, has a flame-spread index of 25 or less and a smoke-developed index of 450 or less when tested in accordance with ASTM E84. Based on large scale tests in accordance with NPFA 286, GacoOnePass Low GWP insulation can be installed at greater thickness as described in Sections 5.3 and 5.4. When insulation is separated from the interior living space of the building with an approved thermal barrier of 1/2 inch thick gypsum board or an equivalent 15-minute thermal barrier complying with, and installed in accordance with, IBC Section 2603.4 or IRC Section R316.4, the maximum thickness is not limited.

4.2 Thermal Resistance: The insulation has thermal resistance (R-value) at a mean temperature of 75°F as shown in Table 2.

4.3 Air Permeability: The insulation, at a minimum thickness of 1 inch, is considered air-impermeable insulation in accordance with IBC Section 1202.3 or IRC Sections R202 and R806.5, based on testing in accordance with ASTM E2178.

4.4 Air Barrier: The insulation, at a minimum thickness of 1 inch, is considered an air-barrier material in accordance with IECC Section C402.5.1.2.1, based on testing in accordance with ASTM E2178.

4.5 Vapor Permeance: The insulation has a moisture vapor permeance of 1 perm at a minimum thickness of 1.70 inches and may be used where a Class II vapor retarder is required by the applicable Code.

5.0 INSTALLATION

5.1 General: GacoOnePass Low GWP F1880 must be installed in accordance with the manufacturer's published installation instructions, the applicable Code, and this Research Report. A copy of the manufacturer's instructions must be available on the jobsite during installation.

5.2 Application: GacoOnePass Low GWP F1880 insulation is spray-applied on the jobsite using a volumetric positive displacement pump as identified in the Gaco Western application instructions. The insulation must be applied when the ambient temperature is greater than 32°F. The insulation must not be used in areas that have a maximum in-service temperature greater than 200°F. The foam plastic must not be used in electrical outlet or junction boxes or in contact with water, rain or soil. The foam plastic must not be sprayed onto a substrate that is wet, or covered with frost or ice, loose scales, rust, oil, or grease. The insulation must be protected from the weather during and after application. The insulation may be applied to the maximum thickness of 5-1/2 inches in a single pass.

5.3 Thermal Barrier:

5.3.1 Application with a Prescriptive Thermal Barrier: GacoOnePass Low GWP F1880 insulation must be separated from the interior occupied space of the building by an approved thermal barrier of 1/2 inch thick gypsum board or an equivalent 15-minute thermal barrier complying with, and installed in accordance with, IBC Section 2603.4 or IRC Section R316.4. Exceptions are provided in Sections 5.3.2 and 5.4.

When the insulation is separated from the interior occupied space of the building with a Code-prescribed thermal barrier, the maximum thickness is not limited.

5.3.2 Application without a Prescriptive Thermal Barrier: GacoOnePass Low GWP F1880 insulation may be installed without the 15-minute thermal barrier prescribed in IBC Section 2603.4 and IRC Section R316.4, when installed in accordance with one of the following options:





Option 1: The thickness of the foam plastic insulation applied to the underside of roof decks, ceilings, or the underside of floors must not exceed 12 inches, and insulation applied to vertical wall surfaces must not exceed 9 inches. The insulation must be covered on all exposed surfaces with DC 315 intumescent coating at an application rate of 0.87 gallons per 100 ft² to achieve a nominal wet film thickness of 14 mils (dry film thickness of 9 mils). The coating must be applied over the insulation in accordance with the coating manufacturer's instructions and this report. Surfaces to be coated must be dry, clean, and free of dirt, loose debris, and other substances that could interfere with the adhesion of the coating. The coating is applied with low-pressure airless spray equipment.

Option 2: The thickness of the foam plastic insulation applied to the underside of roof decks, ceilings, or the underside of floors must not exceed 11 inches, and insulation applied to vertical wall surfaces must not exceed 9 inches. The insulation must be covered on all exposed surfaces with Fireshell F10E intumescent coating at an application rate of 1.12 gallons per 100 ft² to achieve a nominal wet film thickness of 18 mils (dry film thickness of 12 mils). The coating must be applied over the insulation in accordance with the coating manufacturer's instructions and this report. Surfaces to be coated must be dry, clean, and free of dirt, loose debris, and other substances that could interfere with the adhesion of the coating. The coating is applied with low-pressure airless spray equipment.

5.4 Attics and Crawl Spaces: The insulation may be applied in attics and crawl spaces as described in either Section 5.4.1 or 5.4.2. When foam insulation is installed in an attic or crawl space in accordance with this section, a thermal barrier, as described in Section 5.3.1, is not required between the foam plastic insulation and the attic or crawl space but is required between the insulation and the interior living space.

5.4.1 Application with Prescriptive Ignition Barrier: When GacoOnePass Low GWP F1880 insulation is installed within attics and crawl spaces where entry is made only for service of utilities, the ignition barrier must be installed in accordance with IBC Section 2603.4.1.6 or IRC Section R316.5.3 or R316.5.4, as applicable. The ignition barrier must be consistent with the requirements for the type of construction required by the applicable Code and must be

installed in a manner so the foam plastic insulation is not exposed. GacoOnePass Low GWP F1880 insulation as described in this section may be installed in unvented attics in accordance with IBC Section 1202.3 or IRC Section R806.5 at a minimum thickness of 1 inch. The maximum thickness of insulation is as noted in Section 5.4.2.1.

5.4.2 Application without a Prescriptive Ignition Barrier:

5.4.2.1 General: GacoOnePass Low GWP F1880 insulation may be installed in attics and crawl spaces, without the ignition barrier prescribed in IBC Section 2603.4.1.6 and IRC Sections R316.5.3 and R316.5.4, subject to the following conditions:

- a. Entry to the attic or crawl space is only to service utilities, and no storage is permitted.
- b. There are no interconnected attic or crawl space areas.
- c. Air in the attic or crawl space is not circulated to other parts of the building.
- d. Under-floor (crawl space) ventilation is provided when required by IBC Section 1202.4 or 1203.4 or IRC Section R408.1, as applicable.
- e. Attic ventilation is provided when required by IBC Section 1202.2 or IRC Section R806, except when insulation is permitted in unvented attics in accordance with IBC Section 1202.3 or IRC Section R806.5.
- f. Combustion air is provided in accordance with IMC (International Mechanical Code) Section 701 [Sections 701 and 703].

GacoOnePass Low GWP F1880 is an air-impermeable insulation and may be installed in unvented attics, as described in this section, in accordance with IBC Section 1202.3 or IRC Section R806.5 when applied at a minimum thickness of 1 inch.

The insulation may be spray-applied to the underside of the roof sheathing and/or rafters in attics; the underside of wood floors in crawl spaces; and to vertical surfaces in both attics and crawl spaces, as described in this section. The thickness of the foam plastics applied to the underside of the top of the space must not exceed 12 inches, and to vertical surfaces must not exceed 9 inches. The insulation may be installed without prescriptive ignition barrier required by IBC Section 2603.4.1.6 or IRC Section R316.5.3 and R316.5.4 or a protective coating.





5.4.4.2 Use on Attic Floors: GacoOnePass Low GWP F1880 insulation may be installed exposed (no coating) at a maximum thickness of 9 inches between and over the joists in attic floors in accordance with this section and conditions a. through f. of Section 5.4.2.1 based on testing in accordance with AC377, Appendix X. The insulating must be separated from the interior occupied space by an approved thermal barrier. The insulation may be installed without the prescriptive thermal or ignition barrier required by IBC Section 2603.4 and IRC Section R316.5.3 or protective coating.

5.5 Exterior Walls in Types I, II, III, and IV Construction: GacoOnePass Low GWP F1880 may be installed in exterior walls of buildings of Types I, II, III, and IV construction complying with IBC Section 2603.5 and as described in the section. Intertek Design Listings [GWL/FI 30-04](#) and [GWL/FI 30-05](#) describe the assemblies certified by Intertek as complying with NFPA 285. The test wall assemblies were extended to include various wall constructions described in Tables 3 and 4 through a third-party engineering analysis. The potential heat of the foam plastic in any portion of the wall must not exceed 2043 Btu/ft² per inch of insulation thickness. The maximum thickness of insulation is 3-5/8 inches in interior wall cavities and 4 inches on the exterior.

5.6 Duct Insulation: GacoOnePass Low GWP F1880 may be applied to the exterior of residential ducts in attics and crawl spaces in compliance with IRC Section M1601.3. The insulation must be protected in accordance with the ignition barrier requirements of either Section 5.4.1 or 5.4.2.

6.0 CONDITIONS OF USE

6.1 Installation must comply with this Research Report, the manufacturer's published installation instructions, and the applicable Code. In the event of a conflict, this report governs.

6.2 The insulation must be separated from the interior living space of the building by a thermal barrier as described in Section 5.3.1, except as described in Sections 5.3.2 and 5.4.

6.3 The insulation must not exceed the thicknesses noted in Sections 4.1, 5.3, 5.4, and 5.5 as applicable.

6.4 Use of the insulation in Types I, II, III, and IV construction must be as described in Section 5.5.

6.5 Use of the insulation in areas where the probability of termite infestation is "very heavy" must be in accordance with IRC Section R318.4 or IBC Section 2603.8, as applicable.

6.6 The GacoOnePass Low GWP F1880 is manufactured under a quality control program with inspections by Intertek Testing Services NA, Inc.

7.0 SUPPORTING EVIDENCE

7.1 Reports of tests in accordance with ASTM C518, ASTM E84, ASTM E2178, ASTM E96, ASTM C411, NFPA 285, NFPA 286, and NFPA 259.

7.2 Priest & Associates Consulting, LLC Evaluation Report dated November 6, 2017.

7.3 Data in accordance with the ICC-ES Acceptance Criteria for Spray-applied Foam Plastic Insulation (AC 377), dated April 2016, including reports of test in accordance with Appendix X.

7.4 Research Reports for evaluation of data in accordance with ICC-ES Acceptance Criteria for Fire-protective Coatings Applied to Spray-applied Foam Plastic Insulation Installed without a Code-prescribed Thermal Barrier (AC456), dated October 2015.

7.5 Intertek Listing Report "GacoOnePass Low GWP F1880 Spray-applied Polyurethane Foam Insulation", on the [Intertek Directory of Building Products](#).

8.0 IDENTIFICATION

The A and B components of the insulation are identified with the manufacturer's name (Gaco Western, LLC), address and telephone number, the product name (GacoOnePass Low GWP F1880), use instructions, the flame spread and smoke-development indices, the lot number, the Intertek Mark, and the Code Compliance Research Report number (CCRR-1106).





9.0 OTHER CODES

This section is not applicable.

10.0 CODE COMPLIANCE RESEARCH REPORT USE

10.1 Approval of building products and/or materials can only be granted by a building official having legal authority in the specific jurisdiction where approval is sought.

10.2 Code Compliance Research Reports shall not be used in any manner that implies an endorsement of the product by Intertek.

10.3 Reference to the <https://bpdirectory.intertek.com> is recommended to ascertain the current version and status of this report.

This Code Compliance Research Report ("Report") is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this Report. Only the Client is authorized to permit copying or distribution of this Report and then only in its entirety, and the Client shall not use the Report in a misleading manner. Client further agrees and understands that reliance upon the Report is limited to the representations made therein. The Report is not an endorsement or recommendation for use of the subject and/or product described herein. This Report is not the Intertek Listing Report covering the subject product and utilized for Intertek Certification and this Report does not represent authorization for the use of any Intertek certification marks. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek.



545 E. Algonquin Road • Arlington Heights • Illinois • 60005
intertek.com/building





TABLE 1 – PROPERTIES EVALUATED

PROPERTY	2018 IBC SECTION ¹	2018 IRC SECTION ¹	2018 IECC SECTION ¹
Physical properties	Not required	Not required	Not required
Surface-burning characteristics	2603.3	R316.3	Not applicable
Thermal barrier/ignition barrier	2603.4	R316.4	Not applicable
Air permeability	1202.3	R806.5	C402.4 R402.4
Air Barrier	Not applicable	Not applicable	C402.4.1.2.1 C402.5.1.2.2
Vapor retarder	202, 1404.3.1 [1405.3]	R702.7.1 [2012 and 2009 -R601.3]	Not applicable
Thermal resistance	1301	N1101.10	C303.1.1 C303.1.4 R303.1.1 R3031.4
Duct Insulation	Not applicable	N1103.2.1 M1601.3	R403.2.1
Exterior walls of Types I – IV construction	2603.5	Not applicable	Not applicable

¹ Section numbers are for the 2018 Codes



TABLE 2 – THERMAL RESISTANCE (R Values)^{1,2,3}

THICKNESSES (inches)	R-VALUE (°F.ft ² .h/Btu)
1	7.1
2	15
3	22
3.5	26
4	30
5.5	41
6	44
7.25	54
8	59
9.25	68
10	74
11.25	83
12	89

¹ R-values are calculated based on tested K-values at 1 inch and 4 inch thicknesses.

² R-values greater than 10 are rounded to the nearest whole number.

³ To determine R values for thickness not listed:

- a. Between 1 inch and 4 inch can be determined through linear interpolation; or,
- b. Greater than 4 inches can be calculated based on R 7.4/inch





TABLE 3 – NFPA 285 COMPLYING WALLS WITH GACO F1880 ON EXTERIOR

WALL COMPONENTS	MATERIALS
Base wall system Use either 1, 2 or 3	<ol style="list-style-type: none"> 1. Concrete Wall 2. Concrete Masonry wall 3. One layer of 5/8 in. thick Type X gypsum wallboard installed on the interior side of minimum 3-5/8 in. deep, minimum No. 20 gage steel studs spaced a maximum of 24 in. on center (OC) with lateral bracing every 4 ft. vertically.
Floorline Firestopping	Mineral wool (4.0 lb/ft ³ density) friction fit in each stud cavity and at each floorline.
Cavity Insulation Use either 1, 2 or 3	<ol style="list-style-type: none"> 1. None 2. Full cavity depth or less of GacoOnePass Low GWP F1880 applied using sheathing as substrate and covering the width of the cavity and inside of the stud flange. 3. Any noncombustible insulation (batts can be either faced or unfaced).
Exterior sheathing Use either 1 or 2	<ol style="list-style-type: none"> 1. 1/2 in. thick exterior gypsum sheathing 2. 5/8 in. thick Type X exterior gypsum sheathing
Exterior insulation Use either 1 or 2	<ol style="list-style-type: none"> 1. None 2. GacoOnePass Low GWP F1880 with a total maximum thickness of 4 in.
Exterior Veneer Use either 1, 2, 3, 4 or 5	<ol style="list-style-type: none"> 1. Brick: Standard type brick veneer anchors installed a maximum of 24 in. OC vertically in each stud. Maximum 2 in. air gap between exterior insulation and standard nominal 4 in. thick clay brick. 2. Stucco: Minimum 3/4 in. thick, exterior cement plaster and lath. A secondary water resistive barrier can be installed between the exterior insulation and the lath. The secondary water resistive barrier shall not be full-coverage asphalt or butyl-based self-adhered membranes. 3. Minimum 2 in. thick natural stone (granite, limestone, marble and sandstone). Any standard non-open-jointed installation technique can be used. 4. Minimum 1-1/2 in. thick artificial cast stone. Any standard non-open-jointed installation technique can be used. 5. Minimum 1-1/4 in. thick Terra Cotta non-open jointed. Any standard non-open-jointed installation technique can be used.





TABLE 4 – NFPA 285 COMPLYING WALLS WITH GACO F1880 IN WALL CAVITY ONLY

WALL COMPONENTS	MATERIALS
Base wall system Use either 1, 2 or 3	<ol style="list-style-type: none"> 1. Concrete wall 2. Concrete masonry wall 3. One layer of 5/8 in. thick Type X gypsum board installed on the interior side of minimum 3-5/8 in. deep, minimum No. 20 gage steel studs spaced at a maximum of 24 in. with lateral bracing every 4 ft. vertically.
Floorline Firestopping	Mineral wool (4.0 lb/ft ³ density) friction fit in each stud cavity and at each floorline.
Cavity Insulation	1. Full cavity depth or less of GacoOnePass Low GWP F1880 applied using sheathing as substrate and covering the width of the cavity and inside of the stud flange.
Exterior sheathing	5/8 in. thick Type X exterior gypsum sheathing
Exterior wall covering Use either 1 or 2	<ol style="list-style-type: none"> 1. Any noncombustible exterior wall covering material 2. Any combustible exterior wall covering system that has successfully been tested in accordance with NFPA 285.

